

Counts- 20
Material- Ablebond 8390P
Needle- 30 Gauge .0008 Gap


Overall Average- .0091158
Overall % Error- 2.40912 @ 3 Sigma

Screw Type- Shallow
Air Pressure- .25 Bars
Velocity- 55 counts/ms



Conductive Epoxy

216 River Street
Haverhill, MA 01832
phone: 978-374-6451
fax: 978-372-4889
email: sales@dltechnology.com
web: www.dltechnology.com



Average Series 1- .009145
% Error Series 1- 2.3138
11:40 A.M.

Average Series 2- .0091
% Error Series 2- 2.3887
12:00 P.M.

Average Series 3- .0091025
% Error Series 3- 2.5248
12:20 P.M.