

Counts- 18
Material- Dexter QMI-506
Needle- 30 Gauge .0012 Gap


Overall Average- .0092936
Overall % Error- 3.68654 @ 3 Sigma

Screw Type- Shallow
Air Pressure- .2 Bars
Velocity- 55 counts/ms



Conductive Epoxy

216 River Street
Haverhill, MA 01832
phone: 978-374-6451
fax: 978-372-4889
email: sales@dltechnology.com
web: www.dltechnology.com



Average Series 1- .009315
% Error Series 1- 4.471318
11:00 A.M.

Average Series 2- .009313
% Error Series 2- 3.449952
11:30 A.M.

Average Series 3- .009253
% Error Series 3- 3.138362
12:00 P.M.